





96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 1

Received:02/	12/2018	Completed: 02/13/2018	Letter: C	BG	P.O.#: P1800237	Test Report #:	3-24515-0-
Client's	Lot N	o : OF 63222 Date of Mf	a · 12 01 00 Ctv	la: Da	consist Acquesiaht Comp	asition: 1009/ Polyastar u	rith A omilia

Lot No.: OF 63222. Date of Mfg.: 12.01.08. Style: Decoprint Acquanight. Composition: 100% Polyester with Acrylic Identification Coating. Weight: 280 g/sq.m. Density: 40x22 50/167 decitex. (see continuation)

Tested For: Mr. Blaise Humphries

SENFA

1 Rue De Morat

67601 Selestat - FRANCE

Key Test: CA 1237 Sm

225

Tel: 011-33 3 88 85 07 77 Ext:

Fax:

CLIENT'S IDENTIFICATION (continuation):

Thickness: 0.24 mm. Product End Use: For Digital Printing.

T.E. 1993:

V 09/15

NTR 04/16

PC: 1H

/jd SM/mg

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - INTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED:

[x] Initially

[] After 3 dry cleanings

[] After 5 launderings @ 160°F

RESULTS:	Specimen #		Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1 2 3 4 5		0 0 0	0 0 0	5.2 4.6 5.0 5.4 4.3
		Avg:	0		
Fill:	6 7 8 9		0 0 0 0	0 0 0 0 0	5.0 5.4 4.4 4.7 4.3
		Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark):

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum average for warp or fill

Afterglow: (see Note #2 below)

6.0 inches maximum for any individual specimen Char Length:

NOTES:

- 1. An asterisk (*) next to any char length measurement indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd2.
- 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

(Page 1 of 2)

SENF

File Copy







96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 2

Received:02/12/2018 Completed:02/13/2018 Letter: C

BG P.O.#: P1800237

Test Report #:

3-24515-0-

225

Client's

Lot No.: OF 63222. Date of Mfg.: 12.01.08. Style: Decoprint Acquanight. Composition: 100% Polyester with Acrylic

Identification Coating. Weight: 280 g/sq.m. Density: 40x22 50/167 decitex. (see continuation)

Tested For: Mr. Blaise Humphries

SENFA

1 Rue De Morat

67601 Selestat - FRANCE

Key Test: CA 1237 Sm

Tel: 011-33 3 88 85 07 77

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [] Does not comply

REMARKS: None.

The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:

- 1. A maximum afterflame of 4 seconds is permitted as opposed to 1 second.
- 2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement.
- 3. Ten specimens are tested in lieu of 6 specimens.

This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE

GOVMARK /jb

(Page 2 of 2)

Douglas W. Lipp

FEB 2 0 2018

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from Govmark.

File Copy

